

Work Order	3109.2_Rev1
Setup-Code	180611-10290-2801-02



# **Test Report**

JIS Z 2801:2012 (Mod)

Antimicrobial products – Test for antimicrobial activity and efficacy

# **Test Object:**

Coated Leneta-Foil vs. Staph. aureus DSM 21979



Released:

## Test Report JIS Z 2801:2012 (Mod)

Work Order	3109.2_Rev1
Setup-Code	180611-10290-2801-02

# **Report on Findings**

Client: Address:	NANO4LIFE EUROPE L.P. Vouliagmenis Ave. 318 Ag. Dimitrios – 173 43 Athens/Greece
Work order no.:	3109.2_Rev1
Test object:	Coated Leneta-Foil vs. Staph. aureus DSM 21979
Sample description:	Coated Foil
Date of receipt of sam	ple: 08.06.2018
Type of test:	JIS Z 2801:2012 Antimicrobial products – Test for antimicrobial activity and efficacy
Test Germ:	Staphylococcus aureus DSM21979 EDCC 5247
Test laboratory:	QualityLabs BT GmbH
Address:	Neumeyerstrasse 46a 90411 Nuremberg, Germany
Setup-Code:	180611-10290-2801-02
Sample material:	Leneta-Foil
No. of pages in report	: 7
to the client:	lace and date of preparation:  Nuremberg, 17.9.2018  ecipient:  NANO4LIFE EUROPE L.P.  evision of the test report from the 13 <sup>th</sup> of September 2018
Laboratory Director:	Harald Gerauer, Laboratory Director QualityLabs BT GmbH

EN 24.09.2014 TN

Markus Zehe, Managing Director QualityLabs BT GmbH



Work Order	3109.2_Rev1
Setup-Code	180611-10290-2801-02

#### **Declaration on Quality Assurance**

This investigation was performed and supervised according to the standard operating procedure "SOP zu JIS Z 2801:2012 (Mod)" by QualityLabs BT GmbH. The laboratory and process are continually monitored by independent, external authorities, as well as by internal audits.

#### **Archiving**

A copy of the test report, a protocol of the measurement as well as the accompanying correspondence and business records are archived by QualityLabs BT GmbH. The retention period is at least 10 years.

#### **Test description**

Anti-bacterial activity is determined in accordance with a modified version of JIS Z 2801:2012.

During the test, a thin liquid-film containing the bacteria  $(1.25 \times 10^4 \, \text{CFU} \, / \, \text{cm}^2)$  is applied directly to the test sample (Standard: 5 cm x 5 cm). To avoid desiccation a foil (Standard: 4cm x 4cm, Stomacher Bags) is applied. Immediately after inoculation, the bacteria from the reference sample are separated from the sample and the enveloping foil surfaces using ultrasound and vortex devices and the number of viable germs (CFU – colony-forming units) is determined ( $t_0$  value). A further set of reference samples and samples given anti-microbial treatment is incubated with bacteria in a liquid-film and the enveloping foil in a damp environment at 37°C. After 24 hours, the bacteria are separated from the sample surfaces using ultrasound and vortex devices and the number of viable germs is determined ( $t_{24}$  value).



Work Order	2400.2 Pov4
Work Order	3109.2_Rev1
Setup-Code	180611-10290-2801-02

## **Assessment of antimicrobial activity**

A logarithmic germ reduction of ≥ 3 log scales of the antimicrobial sample in comparison to the respective reference is used as assessment criterion to pass the antimicrobial test.

Germ reduktion [log scales]	Antibacterial activity
< 3	Not sufficient antimicrobial activity
≥3	Sufficient antimicrobial activity



Work Order	3109.2_Rev1
Setup-Code	180611-10290-2801-02

#### **References to Testconditions**

Testconditions					
Sample size	25	cm <sup>2</sup>			
Foil size	16	cm <sup>2</sup>			
Volume Inoculum	400	μl			
Sample cleaning	Isopropanol	-			

References to deviations, preincubations, special test conditions

**NONE** 



Work Order	3109.2_Rev1
Setup-Code	180611-10290-2801-02

## **Test Results**

	Sample Name	Sample Code		t <sub>0</sub> (cells/cm <sup>2</sup> )		1	t <sub>24</sub> (cells/cm²)		Reduction [%]	Log Reduction
1	Leneta-Folie P121-10 (Reference)	102900806180001	3.1 x 10 <sup>4</sup>	3.0 x 10 <sup>4</sup>	8.0 x 10 <sup>4</sup>	2.6 x 10 <sup>4</sup>	3.3 x 10 <sup>4</sup>	4.9 x 10 <sup>4</sup>		-
2	NANO4-CLEAN/PRIME NANO4-HYGIENE LIFE	102900806180002				< 1.0 x 10 <sup>1</sup>	< 1.0 x 10 <sup>1</sup>	< 1.0 x 10 <sup>1</sup>	> 99.99	> 4

<sup>\*</sup>see "Interpretation of Results", page 6

Test strain	Staphylococcus aureus DSM21979 EDCC 5247
Initial cell count inoculum / cm²	1.25 x 10⁴
Initials of the editor	JJ
Measurement ended on	Jun-15-2018



Work Order	3109.2_EN
Setup-Code	180611-10290-2801-02

Comments on	4004 0	hiooto
Comments on	Test o	DIECTS

**NONE** 

## Interpretation of the results based on the measurements

**NONE** 

Editor:	Mrs Jovanovic	Crosschecked: Mr Shend	i
Editor.	ivirs Jovanovic	Crosschecked, Mr. Shend	

#### References

JIS Z 2801:2012 Antimicrobial products – Test for antimicrobial activity and efficacy