

Work Order	3109.3_Rev1
Setup-Code	180611-10290-2801-03



## Test Report

### JIS Z 2801:2012 (Mod)

**Antimicrobial products – Test for antimicrobial activity and efficacy**

#### **Test Object:**

*Coated Leneta-Foil vs. Klebsiella pneumoniae DSM 6135*

Work Order	3109.3_Rev1
Setup-Code	180611-10290-2801-03

## Report on Findings

**Client:** NANO4LIFE EUROPE L.P.  
**Address:** Vouliagmenis Ave. 318  
 Ag. Dimitrios – 173 43  
 Athens/Greece

**Work order no.:** 3109.3\_Rev1

**Test object:** Coated Leneta-Foil vs. Klebsiella pneumoniae DSM 6135

**Sample description:** Coated Foil

**Date of receipt of sample:** 08.06.2018

**Type of test:** JIS Z 2801:2012 Antimicrobial products – Test for antimicrobial activity and efficacy

**Test Germ:** Klebsiella pneumoniae DSM6135

**Test laboratory:** QualityLabs BT GmbH

**Address:** Neumeyerstrasse 46a  
 90411 Nuremberg, Germany

**Setup-Code:** 180611-10290-2801-03

**Sample material:** Leneta-Foil

**No. of pages in report:** 7

**Report on findings to the client:** **Place and date of preparation:** Nuremberg, 17.9.2018  
**Recipient:** NANO4LIFE EUROPE L.P.  
 Revision of the test report of the 14<sup>th</sup> of September 2018

**Laboratory Director:** \_\_\_\_\_  
 Harald Gerauer, Laboratory Director  
 QualityLabs BT GmbH

**Released:** \_\_\_\_\_  
 Markus Zehe, Managing Director  
 QualityLabs BT GmbH

Work Order	3109.3_Rev1
Setup-Code	180611-10290-2801-03

---

## Declaration on Quality Assurance

This investigation was performed and supervised according to the standard operating procedure "SOP zu JIS Z 2801:2012 (Mod)" by QualityLabs BT GmbH. The laboratory and process are continually monitored by independent, external authorities, as well as by internal audits.

## Archiving

A copy of the test report, a protocol of the measurement as well as the accompanying correspondence and business records are archived by QualityLabs BT GmbH. The retention period is at least 10 years.

## Test description

Anti-bacterial activity is determined in accordance with a modified version of JIS Z 2801:2012.

During the test, a thin liquid-film containing the bacteria ( $1.25 \times 10^4$  CFU / cm<sup>2</sup>) is applied directly to the test sample (Standard: 5 cm x 5 cm). To avoid desiccation a foil (Standard: 4cm x 4cm, Stomacher Bags) is applied. Immediately after inoculation, the bacteria from the reference sample are separated from the sample and the enveloping foil surfaces using ultrasound and vortex devices and the number of viable germs (CFU – colony-forming units) is determined ( $t_0$  value). A further set of reference samples and samples given anti-microbial treatment is incubated with bacteria in a liquid-film and the enveloping foil in a damp environment at 37°C. After 24 hours, the bacteria are separated from the sample surfaces using ultrasound and vortex devices and the number of viable germs is determined ( $t_{24}$  value).

Work Order	3109.3_Rev1
Setup-Code	180611-10290-2801-03

### Assessment of antimicrobial activity

A logarithmic germ reduction of  $\geq 3$  log scales of the antimicrobial sample in comparison to the respective reference is used as assessment criterion to pass the antimicrobial test.

Germ reduktion [log scales]	Antibacterial activity
< 3	Not sufficient antimicrobial activity
$\geq 3$	Sufficient antimicrobial activity

Work Order	3109.3_Rev1
Setup-Code	180611-10290-2801-03

## References to Testconditions

Testconditions		
Sample size	25	cm <sup>2</sup>
Foil size	16	cm <sup>2</sup>
Volume Inoculum	400	μl
Sample cleaning	Isopropanol	-

## References to deviations, preincubations, special test conditions

NONE

Work Order	3109.3_Rev1
Setup-Code	180611-10290-2801-03

### Test Results

	Sample Name	Sample Code	t <sub>0</sub> (cells/cm <sup>2</sup> )			t <sub>24</sub> (cells/cm <sup>2</sup> )			Reduction [%]	Log Reduction
1	Leneta-Folie P121-10 (Reference)	102900806180001	2.1 x 10 <sup>4</sup>	3.6 x 10 <sup>4</sup>	8.0 x 10 <sup>4</sup>	2.7 x 10 <sup>5</sup>	3.8 x 10 <sup>5</sup>	2.7 x 10 <sup>5</sup>	-	-
2	NANO4-CLEAN/PRIME NANO4-HYGIENE LIFE	102900806180002				6.4 x 10 <sup>2</sup>	7.5 x 10 <sup>1</sup>	< 1.0 x 10 <sup>1</sup>	<b>99.92</b>	<b>3.11</b>

\*see "Interpretation of Results", page 6

Test strain	<i>Klebsiella pneumoniae DSM6135</i>
Initial cell count inoculum / cm <sup>2</sup>	1.25 x 10 <sup>4</sup>
Initials of the editor	JJ
Measurement ended on	Jun-14-2018

Work Order	3109.3_Rev1
Setup-Code	180611-10290-2801-03

---

### Comments on test objects

NONE

### Interpretation of the results based on the measurements

NONE

**Editor:** Mrs. Jovanovic \_\_\_\_\_

**Crosschecked:** Mr. Shendi\_\_\_\_\_

### References

JIS Z 2801:2012 Antimicrobial products – Test for antimicrobial activity and efficacy